

IN THE CLAIMS

1. (Currently Amended) An absorbing composition comprising at least one inorganic-based compound, at least one absorbing compound, and at least one material modification agent, wherein the at least one material modification agent comprises at least one adhesion promoter, at least one crosslinking agent, at least one porogen, at least one catalyst, at least one capping agent, at least one pH tuning agent or a combination thereof.
2. Canceled.
3. (Original) The composition of claim 1, wherein the absorbing compound is an organic-based compound.
4. (Original) The composition of claim 1, wherein the absorbing compound strongly absorbs light over at least an approximately 0.5 nm wide wavelength range at wavelengths less than 375 nm.
5. (Original) The composition of claim 1, wherein the absorbing compound strongly absorbs light over at least an approximately 10 nm wide wavelength range at wavelengths less than 375 nm.
6. (Original) The composition of claim 4, wherein the range comprises wavelengths less than about 260 nm.
7. (Original) The composition of claim 1, wherein the absorbing compound comprises at least one benzene ring and a reactive group selected from the group comprising hydroxyl groups, amine groups, carboxylic acid groups and substituted silyl groups.
8. (Original) The composition of claim 7, wherein the absorbing compound comprises two or more benzene rings.
9. (Original) The composition of claim 8, wherein the two or more benzene rings are fused.
10. (Original) The composition of claim 7, wherein the organic absorbing compound comprises an absorbing compound comprising anthraflavic acid, 9-anthracene carboxylic acid, 9-anthracene methanol, alizarin, quinizarin, primuline, 2-hydroxy-4(3-triethoxysilylpropoxy)-diphenylketone, rosolic acid, triethoxysilylpropyl-1,8-

naphthalimide, 9-anthracene carboxy-alkyl triethoxysilane, phenyltriethoxysilane, 10-phenanthrene carboxy-methyl triethoxysilane, 4-phenylazophenol, 4-ethoxyphenylazobenzene-4-carboxy-methyl triethoxysilane, 4-methoxyphenylazobenzene-4-carboxy-methyl triethoxysilane or mixtures thereof.

11. (Original) The composition of claim 1, wherein the inorganic-based compound comprises a silicon-based compound.
12. (Original) The composition of claim 11, wherein the silicon-based compound comprises a polymer.
13. (Original) The composition of claim 12, wherein the polymer comprises an organosiloxane compound, such as methylsiloxane, methylsilsesquioxane, phenylsiloxane, phenylsilsesquioxane, acrylic siloxane polymers, methylphenylsiloxane, methylphenylsilsesquioxane, silicate polymers, silazane polymers or mixtures thereof.
14. (Original) The composition of claim 12, wherein the polymer comprises hydrogensiloxane, hydrogensilsesquioxane, organohydridosiloxane, silsesquioxane-based compounds, derivatives of silici acid and organohydridosilsesquioxane polymers; copolymers of hydrogensilsesquioxane and an alkoxyhydridosiloxane, hydroxyhydridosiloxane, derivatives of silici acid or mixtures thereof.
15. (Original) The composition of claim 12, wherein the polymer is of a general formula comprising $(H_{0-1.0}SiO_{1.5-2.0})_x$, where x is greater than about 4, and $(H_{0-1.0}SiO_{1.5-2.0})_n(R_{0-1.0}SiO_{1.5-2.0})_m$, where m is greater than 0, the sum of n and m is from about 4 to about 5000 and R is a C₁-C₂₀ alkyl group or a C₆-C₁₂ aryl group.
16. (Currently Amended) The composition of claim [[2]] 1, wherein the at least one adhesion promoter comprises a base.
17. (Currently Amended) The composition of claim [[2]] 1, wherein the at least one adhesion promoter comprises nitrogen.
18. (Currently Amended) The composition of claim [[2]] 1, wherein the at least one adhesion promoter comprises phosphorus.

19. (Original) The composition of one of claims 16 or 17, wherein the at least one adhesion promoter comprises an amine base.
20. (Original) The composition of claim 19, wherein the at least one adhesion promoter comprises ammonium, pyridine, aniline, TMAH, CTAH, TBAH, APTEOS or a combination thereof.
21. (Original) The composition of claim 17, wherein the at least one adhesion promoter comprises at least one amine salt.
22. (Original) The composition of claim 21, wherein the at least one amine salt comprises a weak acid/weak base, a weak acid/strong base or a strong acid/strong base.
23. (Original) The composition of claim 22, wherein the at least one adhesion promoter comprises TMAA, TMAN or a combination thereof.
24. (Original) The composition of claim 22, wherein the at least one amine salt comprises a strong acid/weak base.
25. (Original) The composition of claim 21, wherein the at least one adhesion promoter comprises APTEOS triflate, APTEOS methanesulfonate, APTEOS nitrate, APTEOS nfbs, ammonium triflate, ammonium nfbs, ammonium methanesulfonate, ammonium nitrate, TMAH triflate, TMAH nfbs, TMAH methanesulfonate, TMAH nitrate or a combination thereof.
26. (Currently Amended) The composition of claim [[2]] 1, wherein the at least one adhesion promoter comprises an acid.
27. (Currently Amended) The composition of claim [[2]] 1, the at least one adhesion promoter comprises a neutral compound.
28. (Currently Amended) The composition of claim [[2]] 1, wherein the at least one catalyst comprises a weak acid.
29. (Currently Amended) The composition of claim [[2]] 1, wherein the at least one adhesion promoter comprises a resin-based material.

30. (Original) The composition of claim 29, wherein the resin-based material comprises at least one of a phenolic-containing resin, a novolac resin, an organic acrylate resin or a styrene resin.
31. (Currently Amended) The composition of claim ~~[[2]]~~ 1, wherein the adhesion promoter comprises a polydimethylsiloxane-based material, an alkoxy or hydroxy-containing silane monomer, a vinyl-containing silane monomer, an acrylated silane monomer or a silyl hydride compound.
32. (Currently Amended) The composition of claim ~~[[2]]~~ 1, wherein the at least one capping agent comprises a terminating monomer.
33. (Original) The composition of claim 32, wherein the terminating monomer comprises a silane compound.
34. (Currently Amended) The composition of claim ~~[[2]]~~ 1, wherein the at least one porogen comprises an organic compound.
35. (Original) The composition of claim 34, wherein the organic compound comprises a polymer.
36. (Original) The composition of claim 35, wherein the polymer comprises poly(ethylene oxide).
37. (Currently Amended) The composition of claim ~~[[2]]~~ 1, wherein the at least one porogen further comprises a catalyst.
38. (Original) The composition of claim 37, wherein the catalyst comprises an amine salt.
39. (Original) The composition of claim 38, wherein the amine salt comprises a salt of a weak acid/weak base or a weak acid/strong base.
40. (Original) The composition of claim 37, wherein the catalyst comprises TMAA, TMAN, TBAA, TBAN, CTAA, CTAN or a combination thereof.
41. (Currently Amended) A coating solution comprising the composition of claim 1 ~~one of claim 1 or claim 2~~ and an additional solvent or a solvent mixture.

42. (Original) The coating solution of claim 41, wherein the solution is between about 0.5% and about 20% by weight absorbing material.
43. (Currently Amended) A method of making an absorbing composition comprising:
combining at least one inorganic-based compound, at least one absorbing compound, at least one material modification agent, an acid/water mixture, and one or more solvents to form a reaction mixture, wherein the at least one material modification agent comprises at least one adhesion promoter, at least one crosslinking agent, at least one porogen, at least one catalyst, at least one capping agent, at least one pH tuning agent or a combination thereof; and
allowing the reaction mixture to form the absorbing composition at room temperature.
44. Canceled.
45. (Currently Amended) A method of making an absorbing composition comprising:
combining at least one inorganic-based compound, at least one absorbing compound, at least one material modification agent, an acid/water mixture, and one or more solvents to form a reaction mixture, wherein the at least one material modification agent comprises at least one adhesion promoter, at least one crosslinking agent, at least one porogen, at least one catalyst, at least one capping agent, at least one pH tuning agent or a combination thereof; and
heating the reaction mixture to form the absorbing composition.
46. Canceled.
47. (Currently Amended) A method of making an absorbing composition comprising:
combining at least one inorganic-based compound, at least one absorbing compound, at least one material modification agent, and one or more solvents to form a reaction mixture, wherein the at least one material modification agent comprises at least one acid and water, wherein the at least one material modification agent comprises at least one adhesion promoter, at least one crosslinking agent, at least one porogen, at least one catalyst, at least one capping agent, at least one pH tuning agent or a combination thereof; and
heating the reaction mixture to form an absorbing material, a coating or a film.

48. Canceled.
49. (Currently Amended) A method of making an absorbing composition comprising:
combining at least one inorganic-based compound, at least one absorbing compound, at least one material modification agent, and one or more solvents to form a reaction mixture, wherein the at least one material modification agent comprises at least one acid and water, wherein the at least one material modification agent comprises at least one adhesion promoter, at least one crosslinking agent, at least one porogen, at least one catalyst, at least one capping agent, at least one pH tuning agent or a combination thereof; and
allowing the reaction mixture to form an absorbing material, a coating or a film.
50. Canceled.
51. (Currently Amended) A layered material comprising the absorbing composition of claim 1 ~~one of claims 1 or 2~~ coupled to a resist material.
52. Canceled.
53. (Original) A film comprising the absorbing composition of either of claims 1 or 2.
54. Canceled.
55. (Currently Amended) The composition of claim 1 ~~one of claims 1 or 2~~, wherein the absorbing composition is designed to be at least partially removed.
56. (Original) The composition of claim 51, wherein the resist material absorbs light over a wavelength range that comprises 157 nm, 193 nm, 248 nm and 365 nm.